12AL150 12ALZ150

AMARON QUANTATM

The industrial segment SMF-

is built to perform.

applications

VRLA (Valve Regulated Lead Acid) battery for UPS applications

In short, the lifeline to your UPS

AMARON QUANTA ™ is a product of fail- safe, fool-proof battery technology, produced and tested in our premier manufacturing facility.

Built to the highest technical competence in its class, the

QUANTA is an example of Amara Raja's commitment to bringing the best of technology to your table




Specification

Nominal Voltage		12V				
Rated Capacity		150Ah / C ₂₀ Hr / 1.75VPC / 27°C				
	Length	453 mm (17.83 in.)				
Dimensions (±2mm)	Width	173 mm (6.81 in.)				
	Total Height	251 mm (9.88 in.)				
Weight (±5%)		45.0 Kg (99.21 lbs)				
Terminal Type		M8 x 25mm Copper terminal				
	139.70 Ah	(10hr, 13.97 A, 10.5 V/battery)				
Capacity @ 27°C	128.65 Ah	(5hr, 25.73 A, 10.2 V/battery)				
	95.54 Ah	(1hr, 95.54 A, 9.6V /battery)				
	40°C (104°F)	110%				
Capacity affected	27°C (80.6°F)	100%				
(Temperature at C20 hr rate)	0°C (32°F)	80%				
	-15°C (5°F)	60%				
Case Material	Standard	PPCP (12AL150)				
Case Material	FR Version	UL 94-V0 (12ALZ150)				
Internal Resistance (IR)	Approx. $4.86 \text{ m}\Omega$	for a fully charged battery (27°C)				
Short Circuit Current (As per IEC)		2633 A				
Operating Temp. range	-20°C to +60°C (50 to 60°C for shorter duration)					
Nominal Operating Temp. range		27°C ± 3°C				
	Charging Voltage	13.5 V/battery				
Standby use (27°C)	Charging Current	Max. 25% of rated capacity				
	Temp. Compensation	± 18mV/battery/°C				
	Charging Voltage	13.8 V/battery				
Cyclic use (27°C)	Charging Current	Max. 25% of rated capacity				
	Temp. Compensation	$\pm 30 mV/battery/^{\circ}C$				
Self-Discharge		< 4% per month at 27°C				







93.0 92.5 92.0 91.0

90.0

It features several firsts for the													
battery industry like the unique Radgrid TM		Constant Power Discharge Rating (Watts Per Battery) @ 27°C *											
	ECV/ Time	10min	15min	20min	30min	60min	2hrs	3hrs	5hrs	8hrs	10hrs	20hrs	
	1.60	3594	2801	2269	1817	1125	680	495.0	340.0	225.0	183.0	93.0	
	1.65	3441	2764	2223	1786	1100	670	483.5	325.5	219.0	181.5	92.5	
TERMINAL LAYOUT	1.70	3288	2727	2177	1755	1075	659	470.0	318.0	213.0	180.0	92.0	
	1.75	2125	2600	2127	1724	1050	640	456.0	210.0	210.0	179.5	01.0	

2078

1693

Constant Current Discharge Rating (Amperes) @ 27°C *											
ECV/ Time	10min	15min	20 min	30min	60 min	2 hrs	3 hrs	5 hrs	8hrs	10 hrs	20 hrs
1.60	326.09	258.62	211.26	153.06	95.54	59.08	40.38	27.79	17.24	14.59	8.03
1.65	316.11	250.28	204.31	150.79	94.65	56.69	39.16	26.76	16.87	14.41	7.83
1.70	306.12	241.94	197.36	148.51	93.75	54.29	37.94	25.73	16.49	14.23	7.63
1.75	300.00	238.10	194.80	147.06	91.46	53.57	37.88	25.64	16.39	13.97	7.50
1.80	294.12	230.77	189.80	144.23	89.29	53.19	37.69	25.42	16.30	13.89	7.46

1024

638

442.0

Ø23.1



All dimensions are in mm

1.80

2982

2570

Note:

1. The above data are average values per battery and can be obtained within five charge/discharge cycle

2. A tolerance of ±5% is applicable for the above constant power discharge and constant current discharge values.

3. Recommended to follow IEEE -485 Standard for Battery sizing (In terms of Aging Margin, Design Margin) for Optimal Performance & Life.

4. Considerable Voltage drop across cables, if any shall be considering during battery sizing.



207.0

177.0

302.0



CAUTION

- **Avoid short circuit**
- Don't charge in a sealed container







Performance

A clutch of design features ensures that AMARON QUANTATM

batteries perform predictably and reliably every time

- Proven AGM technology that ensures maintenance free characteristics
- A unique heavy duty corrosion-resistant alloy for positive grids to increase cyclic life in tropical
- RadgridTM profile provides lower internal resistance and superior high-discharge performance
- InstachargeTM a patented paste recipe for excellent charge acceptance
- Low self-discharge rates for extended storage periods
- Design Float life of upto 10 years
- Clean and Sleek looks


Compliance


- JIS C 8702 Certified
- UL (UL-1989) & CE Certified
- Complies to IEC61056 & EUROBAT
- Complies to IS 16220
- Manufactured in ISO 9001, ISO 14001, ISO45001:2018 certified facilities

Applications


- Data Centers
- Banks & Financial Markets
- **Network Operations Centers**
- Industrial Process Control Facilities
- Safety, Surveillance & Security Systems
- Semiconductor Manufacturing
- Power Generation Plants
- Hospital & Testing laboratories

Discharge Characteristics







Shelf Life Characteristics



Temperature Effect on Capacity



Float Service Life vs. Temperature



AMARA RAJA ENERGY & MOBILITY LIMITED

(Formerly Known as Amara Raja Batteries Limited)

CORPORATE OPERATIONS OFFICE:

Terminal A, 1-18/1/AMR/NR, Nanakramguda, Gachibowli, Hyderabad-500032, India, E-Mail: mktg@amararaja.com

REGISTERED OFFICE & Manufacturing Facility-1:

UNIT-I, Karakambadi - 517520, Tirupati, Andhra Pradesh, India, TEL: +91-877-2265000, FAX: +91-877-2285600

Manufacturing Facility-2

UNIT-II, Nunegundlapalle, Bangarupalyam, Chittoor - 517416. Andhra Pradesh, India

